



## AQUAPRO 2770 Water Based Pigment Stain

A water based pigment stain designed to achieve a uniform consistent colour that softens the grain definition providing a colour washed effect. Available in white and pastel colours for lime wash effect.

---

### Advantages

- Versatile – can be applied over all species of timber.
- Medium to Slow dry, easy to apply – results in uniform colour.
- Apply by brush, wiping or applicator before wiping off.
- Can be top coated with AQUAPRO water based, DURAPOL moisture cure, POLYTHANE two pack, NATUROIL oil finishes and FASTASEAL sealers.
- Low odour.
- Non-flammable, no requirements for precautions with oily rags and equipment.
- Water wash up.

---

### Typical Applications

Interior use only. Timber floors, architraves, skirting boards, timber quadrant and beading.

---

### Coverage

Approximately 15 - 25m<sup>2</sup> per litre.

Coverage is determined by application method, the strength of the colour required, timber type, preparation of the surface and the amount of reducer added.

---

### Application Method

By brush, rag or applicator – excess stain must be wiped off with a clean cloth.

- Pad or Rag                      Small areas can be stained with a pad or rag. Use a clean lint free cloth, apply in even strokes
- Applicator                      Flat Pad Applicator
- Brush                              Use to cut in and stain small areas

Ensure that the stain is applied in one continuous application across the whole floor on the same day.

---

### Thinning & Colour Adjustment

When coating a large area, it is recommended that AQUAPRO 2770 Pigment Stain is reduced with either AQUAPRO 1320 Slow Reducer or AQUAPRO 1330 Medium Reducer, this will slow the drying time for easier application.

# AQUAPRO 2770 Pigment Stain

A water based pigment stain for timber

---



**IMPORTANT:** When the stain is reduced the colour will be affected, so it is important to prepare a test area prior to application of the whole area.

AQUAPRO 2770 Pigment Stain can be reduced at any addition rate between 1:1 and 1: 6 (1 Part Stain to 6 Parts Reducer).

Always record the amount of reducer added so the stain can be reproduced in the future.

---

## Dry Time

|                   | Reduced with AQUAPRO 1330<br>Medium Reducer | Reduced with AQUAPRO 1320 Slow<br>Reducer |
|-------------------|---|---|
| <b>Touch Dry:</b> | 2-4 hours                                   | 5-6 hours                                 |
| <b>Recoat:</b>    | 24 hours                                    | 24 hours                                  |

Dry time will be affected by the amount of reducer added and the amount of stain applied. Dry time is also dependent upon ambient temperature and humidity.

To increase the speed of drying, warm air of up to 26°C can be circulated but only after the stain has been applied. Low temperatures, high humidity, damp conditions and lack of airflow will extend drying time.

---

## Application

It is important to apply the stain to one area at a time to ensure an even application. Differences in temperature and environmental effects can result in the stain drying to slightly different colours if it is applied at different times.

Before staining, ensure that all sources of sunlight and heat are removed as this will affect the floor area prior to and during the application of the stain. Seal off any draughts that may cause the stain to dry faster.

### Preparation:

- Prepare a test area to check colour and application.
- Prepare the surface by filling nail holes and imperfections with a water based putty in a colour close to the stain. Allow to dry.
- Sand floor per AS 4786.2-2005 standard to produce a defect and scratch free surface. Finish sanding with 120-180 screen back paper fitted to a rotary sanding machine.
- Ensure floor is defect and scratch free before applying the stain. Scratches and imperfections may be highlighted by the stain.

### Staining:

- Reduce and mix enough stain for the entire project before starting. Work from one corner as you would when coating a room. Apply to strip flooring along the direction of the grain. Only cut in a small distance in front of your applicator. DO NOT pour or pool stain on the floor.
- Excess stain must be wiped off.
- Parquetry – apply the stain in an even application across the narrowest part of the floor from side to side until the whole area is stained.
- Even application of the stain is essential to ensure a uniform even colour.
- Allow the stain to dry before applying coatings (see recoat time).

# AQUAPRO 2770 Pigment Stain

A water based pigment stain for timber



- Ensure adequate coating is applied to seal AQUAPRO 2770 Stain to reduce the risk of sanding through the sealer coat. If this happens, it is possible to reapply the stain to these areas to re-colour the exposed timber.

**First Coat / Sealer product options:** FASTASEAL 3535 or 3030 sealer may be used.

On oily/resinous timbers, Polycure recommends the use of FASTASEAL 3535 for best results.

Do **NOT** use FASTASEAL 3540 over AQUAPRO 2770 Liming Stain.

**Second and Final coat:** Any Polycure coating, AQUAPRO Water Based, DURAPOL Moisture Cure, NATUROIL Oil or POLYTHANE Two Pack.

## Toning / Colouring AQUAPRO Coatings

Add up to 3% (30ml in 1 litre) of AQUAPRO 2770 Stain (unreduced) to the AQUAPRO coating. Mix thoroughly. Apply uniformly to avoid a patchy result.

**IMPORTANT:** adding more than 3% may result in noticeable lap marks. Do not add stain that has been reduced.

|                   |                     |   |  |
|-------------------|---------------------|---|--|
| <b>Properties</b> | <b>Colour</b>       | Liming Wash<br>Puff Haze<br>Greystone<br>Butterscotch | Navajo<br>Ebony<br>Black Japan<br>Merbau |
|                   | <b>Finish</b>       | NA  |  |
|                   | <b>Thinner</b>      | AQUAPRO 1320 Slow or 1330 Medium Reducer              |  |
|                   | <b>Pack Sizes</b>   | 1L & 5L   |  |
|                   | <b>Product Code</b> | 2770  |  |
|                   | <b>Clean Up</b>     | Water or AQUAPRO 1320 or 1330 Reducer                 |  |
|                   | <b>Shelf Life</b>   | 18 months (store in sealed container below 35°C)      |  |

## Health & Safety

Before handling, refer to the Safety Data Sheet for health and safety information. Ensure that all personnel using this product have read and understood this data sheet and the associated SDS and packaging label before using this product.

Note: Coatings give off strong solvents and odours during the drying process. People and pets should be removed from the building during the application and drying of coatings. All food and fabrics should also be removed to reduce the risk of them becoming tainted during the drying process.

ABN 40 000 041 136  
21 Marigold Street, Revesby NSW 2212, Australia, P +61 2 9795 3700 F +61 2 9771 3601  
[sales@mirotone.com.au](mailto:sales@mirotone.com.au)

[www.polycure.com.au](http://www.polycure.com.au)